

Technical Data Sheet

Manufactured in Australia by Foamex, Styroboard XPS offers a range of products available in various sizes and specifications depending on your project requirements. Now contains up to 90% recycled Expanded Polystyrene (EPS).



NOMINAL THERMAL RESISTANCE	R-VALUE R(50/90)	K-VALUE λ(50/90)	TEST METHOD
Thickness 25mm	0.81R	0.031λ	AS-4859.1-2018 / ASTM C518-2017
Thickness 30mm	0.94R	0.031λ	AS-4859.1-2018 / ASTM C518-2017
Thickness 40mm	1.29R	0.031λ	AS-4859.1-2018 / ASTM C518-2017
Thickness 50mm	1.55R	0.033λ	AS-4859.1-2018 / ASTM C518-2017
Thickness 60mm	1.82R	0.033λ	AS-4859.1-2018 / ASTM C518-2017
Thickness 75mm	2.15R	0.034λ	AS-4859.1-2018 / ASTM C518-2017

COMPRESSIVE STRESS Measured parallel to rise (min.)	2%	10%	YIELD	TEST METHOD
Thickness 25mm	>60kPa	>250kPa	>150kPa	AS-2498.3 // ASTM D1621
Thickness 30mm	>90kPa	>250kPa	>200kPa	AS-2498.3 // ASTM D1621
Thickness 40mm	>150kPa	>350kPa	>220kPa	AS-2498.3 // ASTM D1621
Thickness 50mm	>230kPa	>350kPa	>250kPa	AS-2498.3 // ASTM D1621
Thickness 60mm	>240kPa	>350kPa	>280kPa	AS-2498.3 // ASTM D1621
Thickness 75mm	>280kPa	>350kPa	>350kPa	AS-2498.3 // ASTM D1621

FLAME PROPOGATION CHARACTERISTICS	RESULTS	TEST METHOD
Ignitability Index	0 Range 0 - 20	AS-1530.3-1999
Spread of Flame	0 Range 0 - 10	AS-1530.3-1999
Heat Evolved Index	0 Range 0 - 10	AS-1530.3-1999
Smoke Developed index	3 Range 0 - 10	AS-1530.3-1999
Median Flame Duration Max	1.5 seconds	AS-2122.1
Eighth value max.	2.5 seconds	AS-2122.1
Median Volume Retained	≥ 70%	AS-2122.1 Method A
Eighth Value in Volume Min	≥ 60%	AS-2122.1 Method A

PROPERTIES OTHER	RESULTS	TEST METHOD
Rate of vapour transmission, max. measured parallel to rise at 23°C DCSO	100 - 200 μg/m ² s	AS-2498.5
Max. dimensional stability of length, width and thickness, 7 days at 70°C, DCSO	1%	AS-2488.6
Water absorption max.	<0.5% vol/vol	AS-2498.8

The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application, this data does not relieve the purchaser of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.